

High performance 50 micron multimode fibers optimized for 850 nm 10 Mb/s through 10 Gb/s laser-based applications.

Overview

LaserWave® Laser-Optimized Multimode Fibers extend the application of multimode fiber to support transmission speeds of 10 Gb/s and beyond. Using low cost 850 nm Vertical Cavity Surface Emitting Laser (VCSEL) transceivers, these fibers support such applications as 10 Gigabit Ethernet, 10 Gigabit Fiber Channel, and the Optical Internetworking Forum (OIF).

Used in low-loss cabling systems, LaserWave can provide extended reach beyond the rated length, as well as more connections and greater power margins.

Product Description

LaserWave 550 Fiber extends the system cost benefits of LaserWave Fibers to ultra long building backbones and medium length campus backbones. It supports 10 Gb/s Ethernet, Fibre Channel, and OIF applications to 550 meters or more using low cost 850 nm VCSELs. The OFS patented MCVD process provides this extraordinary performance by producing a fiber with nearly zero differential mode delay and 4700 MHz-km of EMB, more than double the IEEE requirement for 10 Gb/s 300 meter support.

LaserWave 300 Fiber is designed specifically to support 300 meter link lengths for 10 Gb/s applications. LaserWave 300 Fiber features a DMD controlled core that assures 10 Gb/s support with 850 nm serial applications for distances of up to 300 meters. Its industry-standard 50 µm core size supports legacy applications like Ethernet, Token Ring, Fiber Distributed Data Interface (FDDI), and Fast Ethernet. The 50 µm core size is also directly compatible with laser-based applications like Gigabit Ethernet, providing support up to 1000 meters for low cost 850 nm VCSEL-based Gigabit Ethernet (1000BASE-SX) applications. The fibers also extend the reach of increasingly popular 2.5 Gb/s parallel applications.

Features/Benefits:

- Provides seamless migration from 10 Mb/s to 10 Gb/s with no cabling system changes up to 550 meters
- Enables lowest cost for legacy applications through 10 Gb/s and beyond, reducing optical system cost by 35% or more
- Saves time, using a single fiber type that speeds cabling system administration and stands ready to support 10 Gb/s upgrades
- Eliminates cumbersome and expensive mode-conditioning patch cords required for 1300 nm laser operation on traditional multimode fibers
- Uses the same low cost connectors and installation practices as traditional multimode fiber.

Flex-10™ Coating for Multimode Fiber

OFS multimode fibers are made with a world-class draw process and our enhanced Flex-10 coating, designed to minimize induced attenuation that can occur in tight-buffer cable. Easy to strip and install, the coating offers outstanding performance in attenuation-sensitive 1 Gb/s and 10 Gb/s systems.

Applications

LaserWave Multimode Fiber is designed to enable low cost 10 Mb/s through 10 Gb/s connectivity for applications such as:

- Local Area Networks
- Storage Area Networks
- Equipment Rooms
- Data Centers
- Central Offices.

Manufacturing and Quality Control

LaserWave Fiber provides improved performance above the minimum required by the standards. OFS' advanced MCVD process used to manufacture LaserWave Fibers eliminates the center defect problems that can plague fibers manufactured with other processes. The Inner DMD mask for LaserWave Fiber is expanded to a range from 0 to 18 μm radius versus the less stringent 5 to 18 μm radius allowed by TIA and IEC.

This reduces fundamental and very low-order mode DMD for improved operating margin and superior support of concentrated center-launch lasers. This results in LaserWave Fiber DMD up to 60% better than what the standard allows in the center portion of the fiber and improves system reliability margins versus other DMD controlled fibers.

OFS LaserWave Fiber specifications exceed the reliability requirement of the IEEE 10 Gigabit Ethernet standard, providing assurance for 100% functional system reliability.

Product Specifications

Physical Characteristics		50/125
Core Diameter		$50 \pm 2.5 \mu\text{m}$
Core Non-Circularity		$\leq 5 \%$
Clad Diameter		$125 \pm 1 \mu\text{m}$
Clad Non-Circularity		$\leq 1 \%$
Core/Clad Concentricity Error (Offset)		$\leq 1.0 \mu\text{m}$
Coating Diameter		$245 \pm 10 \mu\text{m}$
Coating Non-Circularity		$\leq 5 \%$
Coating-Clad Concentricity Error (Offset)		$\leq 8 \mu\text{m}$
Tensile Proof Test		100 kpsi (0.69 GPa)
Coating Strip Force		Range: 0.5 - 1.0 lbf (2.2 - 4.4 N) Typical: 0.7 lbf (3.0 N)
Standard Reel Lengths		2.2 – 8.8 km
Optical Characteristics		
Attenuation		
at 850 nm		$\leq 2.3 \text{ dB/km}$
at 1300 nm		$\leq 0.6 \text{ dB/km}$
Laser Bandwidth/EMB		<i>See Transmision Characteristics Table</i>
Transmission Distance (Link Length) Support		<i>See Applications Support Table</i>
Attenuation at 1380 nm minus attenuation at 1300 nm		$\leq 1.0 \text{ dB/km}$
Attenuation Uniformity / Point Discontinuities at 850 nm and 1300 nm		$\leq 0.08 \text{ dB}$
Numerical Aperture		0.20 ± 0.015
Chromatic Dispersion		
Zero Dispersion Wavelength (λ_0)		1295 – 1340 nm
Zero Dispersion Slope (S_0)		$\leq 0.105 \text{ ps/nm}^2\text{-km}$ ($1295 \leq \lambda_0 \leq 1310 \text{ nm}$) $\leq 0.000375 \times (1590 - \lambda_0)$ ($1310 \leq \lambda_0 \leq 1340 \text{ nm}$)
Group Refractive Index		
at 850 nm		1.483
at 1300 nm		1.479
Backscatter Coefficient		
at 850 nm		-68.4 dB
at 1300 nm		-75.8 dB
Macrobend Attenuation		
100 turns on a 75 mm mandrel at 850 nm and 1300 nm		$\leq 0.5 \text{ dB}$
Environmental Characteristics		
Operating Temperature Range		-60° C to +85° C
Temperature Induced Attenuation at 850 nm and 1300 nm from -60° C to +85° C (5 24-hour cycles)		$\leq 0.1 \text{ dB/km}$
Temperature and Humidity Induced Attenuation at 850 nm and 1300 nm from -10° C to +85° C, 94% RH (30 24-hour cycles)		$\leq 0.1 \text{ dB/km}$
Accelerated Aging (Temperature) Induced Attenuation at 85° C for 30 days		$\leq 0.1 \text{ dB/km}$
Water Immersion Induced Attenuation, 23° C for 30 days		$\leq 0.1 \text{ dB/km}$
Dynamic Fatigue Stress Corrosion Parameter (n_d)		≥ 18

Transmission Characteristics

Minimum Bandwidth Specifications (MHz-km)

Wavelength (nm)	LaserWave Fiber		Typical 50 μm fiber	Typical 62.5 μm fiber
	550	300		
Laser EMB @ 850 nm ¹	4700	2000	Not Specified	Not Specified
Laser EMB @ 1310 nm	500	500	Not Specified	Not Specified
Overfilled @ 850 nm ²	3500	1500	500	200
Overfilled @ 1300 nm ²	500	500	500	500

¹ Effective Modal Bandwidth, per TIA/EIA-492AAAC and IEC 60793-2-10 for type A1a.2, ensured by DMD performance specifications for sources meeting launch conditions specified in 10 Gigabit Ethernet (IEEE 802.3ae), OIF OC-192/STM-64 VSR-4-04, and 10 Gigabit Fibre Channel (10GFC).

² Measured per TIA/EIA-455-204

DMD Specifications³ (ps/m maximum)

The fiber shall meet at least one of the following 6 DMD Templates, which each consists of both an inner and outer mask specification, and the sliding mask specifications shown at below.

The requirements for LaserWave 300 are compliant with, but more stringent than the requirements of TIA-492AAAC, "Detail specification for 850-nm laser-optimized, 50- μm core diameter/125- μm cladding diameter class Ia graded-index multimode optical fibers."

Template Number	850 nm DMD-Inner Mask (ps/m) (Radius 0-18 μm) ^{1,2}	850 nm DMD-Outer Mask (ps/m) (Radius 0-23 μm) ²
1	≤ 0.23	≤ 0.70
2	≤ 0.24	≤ 0.60
3	≤ 0.25	≤ 0.50
4	≤ 0.26	≤ 0.40
5	≤ 0.27	≤ 0.35
6	≤ 0.33	≤ 0.33

¹ OFS Inner Mask Radial specification is more stringent than the TIA/EIA-492AAAC requirement of 5-18 μm .

² OFS DMD measurement scanning steps are 1 μm , twice as stringent as the maximum 2 μm steps required by the TIA-FOTP-220 standard.

³ Measured per DMD test methods TIA/EIA-455-220 and IEC 60793-1-49.

Note: Based on the TIA/EIA-492AAAC standard, the minimum effective modal bandwidth-length product for LaserWave fiber is ensured by combining this 50 μm fiber with transmitters having a transmitter center wavelength (λ_c) meeting: $840 \leq \lambda_c \leq 860$ nm, and the following transmitter power distribution (per FOTP-203): Encircled Flux at radius 4.5 $\mu\text{m} \leq 30\%$, and Encircled Flux at radius 19 $\mu\text{m} \geq 86\%$.

For more information on DMD, visit our website at www.ofsoptics.com and download our white paper, *Measuring Bandwidth of High-Speed Multimode Fiber*.

Sliding Mask Specifications

In addition to meeting the DMD requirements of the table, LaserWave 300 fiber is the first to meet the new requirement that the maximum DMD mask width over any 6 μm interval between 7 and 19 μm offset positions shall be less than or equal to 0.25 ps/m:

Radial Interval	Mask Width (ps/m)
7-13 μm	≤ 0.25
8-14 μm	≤ 0.25
9-15 μm	≤ 0.25
10-16 μm	≤ 0.25
11-17 μm	≤ 0.25
12-18 μm	≤ 0.25
13-19 μm	≤ 0.25

Applications Support

Application Support Examples Distance (Meters)¹

	LaserWave Fibers		Typical 50 μ m	Typical 62.5 μ m
	550	300	500/500 MHz-km	200/500 MHz-km
10 Gigabit Ethernet (802.3ae)				
850 nm serial laser (10GBASE-SR) & (10GBASE-SW)	550 ²	320	82	33
1310 nm CWDM lasers (10GBASE-LX4)	300	300	300	300
Mode conditioning patch cord required for LX4?	No	No	Yes	Yes
1 Gigabit Ethernet				
850 nm serial laser (1000BASE-SX)	1040	970 ³	550	275
1310 nm serial laser (1000BASE-LX)	600	600	550	550
Mode conditioning patch cord required for LX?	No	No	Yes	Yes
100 Megabit Ethernet				
850 nm serial LED (100BASE-SX)	300	300	300	300
1310 nm serial LED (100BASE-FX)	2000	2000	2000	2000
10 Megabit Ethernet				
850 nm LED (10BASE-FL)	1250	1250	1250	2000
10 Gigabit Fibre Channel (10GFC Rev 3.0)				
850 nm serial laser (1200-M5E-SNS)	530 ²	320	82	33
1310 nm WWDM lasers (1200-M5-LC4S)	300	300	300	300
Mode conditioning patch cord required for LC4S?	No	No	Yes	Yes
1 Gigabit Fibre Channel				
850 nm serial laser (100-Mx-SNI)	970	920	500	300
10 Gigabit OIF OC-192 VSR				
850 nm serial (VSR-4-04)	550 ²	330	82	32
850 nm 4x2.5 Gb/s parallel (VSR-4-03) ⁴	700	620	250	120

¹ Unless otherwise indicated, application support distances are based on standard total connection plus splice loss of 1.5 dB and cable attenuations of 3.5/1.5 dB/km at 850 nm and 1300 nm respectively. Lower-loss connectors, such as LCs, and lower cable attenuations can lead to longer supportable distances. Contact OFS for specific cable attenuation and connection plus splice loss necessary to support a target distance.

² Reach assuming 3.5 dB/KM maximum cabled attenuation at 850 nm plus 1.0 dB of total connection and splice loss, or 3.0 dB maximum cabled attenuation at 850 nm and 1.3 dB total connection and splice loss.

³ 1000-meter reach assuming total connection plus splice loss of 0.9 dB.

⁴ Assumes 1.5 dB of connection plus splice loss. Requires use of array connectors such as MTP or MPO.

For additional information please contact your sales representative.

You can also visit our website at:

www.ofsoptics.com/ofsfiber or call 1-888-fiberhelp (from inside the USA).

For regional assistance, contact the global location closest to you.



A Furukawa Company

LaserWave is a registered trademark and Flex-10 is a trademark of Furukawa Electric North America. OFS reserves the right to make changes to the prices and product(s) described in this document in the interest of improving internal design, operational function, and/or reliability. OFS does not assume any liability that may occur due to the use or application of the product(s) and/or circuit layout(s) described herein. This document is for informational purposes only and is not intended to modify or supplement any OFS warranties or specifications relating to any of its products or services.

Copyright © 2008 Furukawa Electric North America. All rights reserved, printed in USA. OFS Marketing Communications / fiber-116-0108

North America

Telephone: 508-347-8590
Toll Free: 800-799-7732
Fax: 508-347-1211
E-mail: fibersalesnar@ofsoptics.com

Asia Pacific

Telephone: +852 2836 7102
Fax: +852 2836 7101
E-mail: fibersalesap@ofsoptics.com

Caribbean, Latin America

Telephone: +1-508-347-8590
Fax: +1-508-347-1211
E-mail: fibersalescala@ofsoptics.com

Japan

Telephone: +81-3-3286-3424
Fax: +81-3-3286-3708 or 3190
E-mail: fibersalesjapan@ofsoptics.com

Europe, Middle East, Africa

Telephone: +45-43 48 3736
Fax: +45 4348 3444
E-mail: ofssalesdk@ofsoptics.com

China

Telephone: +86 10 6505 3660
Fax: +86 10 65059515
E-mail: fibersaleschina@ofsoptics.com